

SOLIDKOTE 230 E-TAR

High Build Epoxy Tar Coating

Solvent-free, heavy-duty epoxy tar with excellent chemical resistance, grip and flexibility.

UNIQUE PRODUCT BENEFITS

- Excellent chemical resistance.
- Good impact resistance and flexibility.
- Solvent free, no impulsive fumes.
- Cures at low temperatures.
- Can be used as a mortar for paving with the addition of aggregate.

APPLICATIONS

- Highly chemical resistant epoxy coating.
- Linings of storage tanks, sewerage plants, effluent sumps and pumps.
- Coatings on steelwork machinery, piping, concrete structures, floors and woodwork.
- Any surface one wishes to protect against attack by corrosive chemicals and gases.
- Mixed with aggregate for road paving.

SUBSTRATE REQUIREMENTS

All surfaces to be clean, dry and sound in accordance with Solidkote surface preparation specification for the substrate to be coated. Abraded surfaces improve adhesion. Holes in the concrete substrate to be filled with **Solidbond 110**, an epoxy putty or mortar. Holes in wood or steel to be filled with **Solidbond 20S** or **Solidbond QSP**. Solidkote 230 E-Tar is self-priming, it is therefore recommended to apply two coats at 250 µm each.

TECHNICAL DETAILS

No. of Components	2
Mixing Ratio	1:1 Epoxy : Activator
Pot Life @ 25°C	45 min.
Cure Time - Touch Dry	6 to 8 hrs
Practical Dry	24 hrs
Full Cure	7 days
Applied by	Brush / Roller
Theoretical Coverage	3 - 4 m ² / L
Application Temperature	Min 10°C Max 30°C
Temperature Resistance	60°C Wet 80°C Dry
Recommended no. of coats	2
D.F.T. per coat @ 4 m ² / L	250 microns
Overcoat Time	8 hrs min / 48 hrs max
Volume Solids	100%
Shelf Life	12 months

Leading manufacturers of specialist epoxy and polyurethane flooring systems, specialised construction and corrosion protection products.

Distribution facilities nationwide

Western Cape
+27 (0)21 535 4455

Eastern Cape
+27 (0)41 451 3944

Gauteng
+27 (0)11 822 7242

KwaZulu-Natal
+27 (0)31 705 7733



info@technicalfinishes.com • www.technicalfinishes.com



TECHNICAL FINISHES
SPECIALIST FLOORING AND CONSTRUCTION SOLUTIONS

APPLICATION

Stir the contents of the two containers well. Using volumes strictly in accordance with the given mixing ratio, mix the contents of the two containers together for 5 minutes using a mechanical mixing tool.

On areas continuously wet or where fats, oils or grease are present, a non-slip surface can be provided by sprinkling an amount of aggregate into the uncured primer or first coat. Before over coating, sweep off excess aggregate with a stiff nylon broom. Should over 18 hours have elapsed between coats, abrade the surface and wipe with Epoxy Thinners. If the material is left in the container it will become unusable within half an hour. Do not apply if relative humidity exceeds 85%.

HEALTH AND SAFETY

Please read Safety Data Sheet and specific health and safety data for this product provided in compliance with the requirements of OHSA No.85 of 1993.

WARRANTY

Technical Finishes products are manufactured under high quality standards and are warranted against defective materials and are sold subject to standard Terms and Conditions of Sale, copies of which can be obtained upon request. Technical Finishes deals with approved applicators and carry a back to back warranty with these clients. Technical Finishes cannot be held responsible for the workmanship in surface preparation and application of our products, it is understood that the approved contractor will guarantee such workmanship and application. It is vital that the application is done in accordance to our specification.

***Leading manufacturers of specialist epoxy and polyurethane flooring systems,
specialised construction and corrosion protection products.***

Distribution facilities nationwide

Western Cape

+27 (0)21 535 4455

Eastern Cape

+27 (0)41 451 3944

Gauteng

+27 (0)11 822 7242

KwaZulu-Natal

+27 (0)31 705 7733



TECHNICAL FINISHES
SPECIALIST FLOORING AND CONSTRUCTION SOLUTIONS



info@technicalfinishes.com • www.technicalfinishes.com